

Product 07092101-104 Solid glass beads for producing slip resistant coating surfaces

1 General data

Application field

VIASOL Micropearls are used as filler for seal coats and top coats based on epoxy or polyurethane resins.

Product description

VIASOL Micropearls are solid glass beads made of soda lime glass in different grading curves for producing slightly slip resistant and abrasion resistant surfaces.

The corresponding grading curves are added as a filler in the seal coats and thin-layer coatings.

Application

VIASOL Micropearls are mixed in the fresh seal coats and thin-layer coatings based on epoxy- or polyurethane resins in a defined mixing ratio. The processing technology depends on the used product and the used grading curve. The consumption and application technique of the individual system could be found in the relevant installation instructions or system calculations.

Indicative consumptions:

Seal coats (PU/EP) ca. 100 – 150 g/m² f.e. VIASOL PU-S6000P, PU-S6000, PU-S6000 und PU-S6000P

VIASOL Micropearls:	45-90 µm	ca. 5 % p. weight
	90-150 µm	ca. 5 % p. weight

Application tool: microfiber roller 6mm

Stir in the container and stir again before pouring on the surface, as the glass beads in the container can settle down. Spread with the microfiber roll and finish in one direction. Leave no rest or remainings. The end result corresponds to the appearance during application.

Thin layer coatings (PU/EP) ca. 180 – 300 g/m² f.e. VIASOL Urea 6400, Urea 6400P oder VIASOL EP-T712

VIASOL Micropearls:	200-300 µm	ca. 20 % p. weight
	300-400 µm	ca. 25 % p. weight

Application tool: smoothing trowel and structure roller

Grind and clean the previous layer to avoid wetting problems. Mix the glass beads in the container and stir again before pouring on the surface, as the glass beads in the container can settle down. Use the trowel to pull over the grain. Avoid defects and puddling. Distribute with the structure roller and finish in one direction.

Technical support

For further information relating to VIASOL products, please contact VIACOR Polymer GmbH directly.

Phone: +49 (0)7472-949990

E-Mail: info@viacor.de

Manufacturer:

VIACOR Polymer GmbH, Graf-Bentzel-Str. 78, D-72108 Rottenburg, Tel: +49/7472-94999-0, info@viacor.de, www.viacor.de

Product 07092101-104 Solid glass beads for producing slip resistant coating surfaces

Warnings and precautions

Information relating to the safe handling of this product can be found in the Material Safety Data Sheet. Local regulations concerning the safe handling of cleaning materials must be observed. Suitable protective clothing must be worn. Please note that spilled microbeads causes a slippery surface.

Disclaimer

All information in this technical data sheet is based on our current knowledge and experience. This does not release the applicator from performing their own tests as many application factors, beyond our control, affect the application of our product. No guarantee of characteristics or suitability for a special purpose can be derived from this information. All present data, descriptions, drawings, photos, ratios, weights etc. are subject to change without prior notice and do not represent contracted characteristics of the product. Due to different materials, sub-bases and working conditions, no guarantee of an application result or any liability claims can be derived from these details or from an unwritten technical advice except for liability claims based on:
 -damage to life, body or health resulting from a negligent violation of obligations or a deliberate or negligent violation of obligation of a legal representative or assistant and
 -if we are charged with intention or gross negligence.

The user has to test the products for their intended use. The user is responsible for following existing laws and orders and for observing third party trade mark rights.

As all VIACOR data sheets are updated on a regular basis it is the users responsibility to obtain the most recent issue (see www.viacor.de or contact us directly).

(A) Technical data		
Solid product		
1. Solid content		100 %
2. Bulk density	45-90 µm	1.35 g/cm ³
	90-150 µm	1.40 g/cm ³
	200-300 µm	1.44 g/cm ³
	300-400 µm	1.46 g/cm ³
3. Density		in middle 1.41 g/cm ³
4. Hardness		Mohs ≥ 6
5. Package size		25 kg sacs or 1 kg pail
6. Shelf life (20 °C)		36 month
7. Storage		dry at 5 – 25°C

Manufacturer:

VIACOR Polymer GmbH, Graf-Bentzel-Str. 78, D-72108 Rottenburg, Tel: +49/7472-94999-0, info@viacor.de, www.viacor.de