

Product 1022-KAL 2-comp. polyurea wear coat for VIASOL *DECK rapid M*

1 General Data

Fields of application

VIASOL UREA S6001P is used as a weather and color stable, colored wear coat. VIASOL UREA S6001P can be used indoors and outdoors and hardens glossy.

Product Description

VIASOL UREA S6001P is a solvent-free, low-emission, weather and color-stable, 2-component sealant based on aliphatic polyurea. When cured, the product has very good abrasion resistance, very good weather and color stability and is characterized by tough properties.

It has good resistance to dilute acids and bases, lubricants and fuels. Depending on the chemical load, optical discoloration can occur that does not impair the technical usability of the flooring.

VIASOL UREA S6001P has a low tendency to get dirty and is easy to clean.

Properties

- low emission, solvent free
- weathering and colour stable
- abrasion resistant
- glossy

VIASOL systems

VIASOL UREA S6001P is the wear coat within the system:
VIASOL *DECK rapid M*

Care and maintenance

For a long-term preservation of the properties of resin floors, we recommend a regular cleaning and care programme. For further details see our VIASOL Care and Maintenance Guide. Before first use we recommend to perform a basic cleaning and initial care.

Technical support

For system build up possibilities and detailed information relating to the laying of VIASOL products, please refer to the VIASOL System Planner or contact VIACOR Polymer GmbH directly.

Phone: +49 (0)7472-949990

E-Mail: info@viacor.de

(A) Technical Data	
Liquid mixture (A+B)	
1. Viscosity (23 °C)	ca. 8000 - 9000 mPas
2. Density (20 °C)	ca. 1.4 g/cm ³
3. Packaging size (2-component container)	25 kg (22,3 kg A + 2.7 kg B)
4. Color	VIASOL standard, others on request
5. Shelf life (20 °C)	12 months in originally closed container
6. Storage	Dry at 10-25°C, avoid direct sunlight, protect from freezing

(B) Technical Data	
Cured material	
1. Adhesive strength (EN ISO 4624)	> 2.0 N/mm ²
1. Hardness Shore-D (EN ISO 868)	approx. D78
2. Wear resistance EN ISO 5470-1	<700 mg (Taber H22)

Manufacturer:

VIACOR Polymer GmbH | Graf-Bentzel-Str.78 | 72108 Rottenburg | Germany | Tel: +49 7472 94999-0 | info@viacor.de | www.viacor.de

Product 1022-KAL 2-comp. polyurea wear coat for VIASOL *DECK rapid M*

2 Application Method

Please refer also to our general application guideline.

Application

The product is supplied in coordinated quantities in two-component containers. The B component must be completely emptied into the A component. Both components should be mixed homogeneously with a suitable electric stirrer for at least 3 minutes. Avoid mixing in air. We recommend batch-based processing to avoid differences in color. When processing several batches on one construction site, the last containers of the first batch must be mixed together with the first containers of the next batch.

VIASOL UREA-S6001P is spread evenly over the surface with a trowel. The processing time at 20 ° C and 50% rel. At room temperature, air humidity is max. 10 mins. Higher temperatures and higher humidity shorten the processing time. We recommend re-rolling the product to repair imperfections or knocks.

VIASOL SO-X14 tool cleaner is used to clean tools and other dirt.

Over coating

When overworking up to 18 hours after installation, the top layer does not have to be sanded separately. A later revision is only possible after careful grinding.

(B) Technical Data

Liquid mixture (A+B)

1.	Mixing ratio A : B	100 : 12 (% by weight)
2.	Material consumption	2500 – 3000 g/ m ²
3.	Working time (20 °C)	approx. 20 minutes
4.	Application temperature	5 – 30 °C (min. 3°C above dew point)
5.	Relative humidity	40 to max. 85%
6.	Foot traffic (20 °C)	after 8 hours (depending on film thickness)
7.	Following layer (20°C)	within 18 hours
8.	Fully capable of with-standing stress	After 1 day

Manufacturer:

VIACOR Polymer GmbH | Graf-Bentzel-Str.78 | 72108 Rottenburg | Germany | Tel: +49 7472 94999-0 | info@viacor.de | www.viacor.de

Product 1022-KAL 2-comp. polyurea wear coat for VIASOL**DECK rapid M**

3 Further Information

CE-Mark



CE-Mark according to EN 1504-2

For details see CE-conformity mark and declaration of performance.

CE-Mark according to EN 13813

EN 13813: 2003-01, Screed material and floor screeds - Screed materials - Properties and requirements is the basis for requirements for floor screeds used in indoor flooring constructions. Resin coatings and sealer are also subject to this norm.

Details see CE-conformity mark and declaration of performance.

Decopaint-Guidelines (EU 2004/42/EG)

The maximum allowable VOC content for Product Category IIA j Type Lb products (in the ready to use state) is:

Stage II (from 2010) < 500 g/l VOC

In the ready to use state, this product contains less than 500 g/l VOC.

Warnings and precautions

Information relating to the safe handling of this product can be found in the Material Safety Data Sheet. Local regulations concerning the safe handling of epoxy resin based coating materials must be observed.

Suitable protective clothing including suitable eye protection must be worn.

Disclaimer

All information in this technical data sheet is based on our current knowledge and experience. This does not release the applicator from performing their own tests as many application factors, beyond our control, affect the application of our product. No guarantee of characteristics or suitability for a special purpose can be derived from this information. All present data, descriptions, drawings, photos, ratios, weights etc. are subject to change without prior notice and do not represent contracted characteristics of the product.

Due to different materials, sub-bases and working conditions, no guarantee of an application result or any liability claims can be derived from these details or from an unwritten technical advice except for liability claims based on:

-damage to life, body or health resulting from a negligent violation of obligations or a deliberate or negligent violation of obligation of a legal representative or assistant and
-if we are charged with intention or gross negligence.

The user has to test the products for their intended use. The user is responsible for following existing laws and orders and for observing third party trade mark rights.

As all VIACOR data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see www.viacor.de or contact us directly).

Manufacturer:

VIACOR Polymer GmbH | Graf-Bentzel-Str.78 | 72108 Rottenburg | Germany | Tel: +49 7472 94999-0 | info@viacor.de | www.viacor.de