

PORPLASTIC *olympic gold* - world-class sports surface

Massive, one or multilayer full PU-bound system, all layers with coloured EPDM granules, water-impermeable

SYSTEM LAYERS

line paint:

PORPLASTIC X8090

UV-sealing (optional):

PORPLASTIC S6020

structured cast coating (ca. 3 - 5 mm):

PORPLASTIC C570 spread with
PORPLASTIC EPDM 1 – 4 mm

2 x cast coating (ca. 5 mm per layer):

PORPLASTIC C570 spread with
PORPLASTIC EPDM 1 – 4 mm

primer:

PORPLASTIC P270 recommended for asphalt
VIASOL EP-P210 for concrete, small areas, curbs

bound sub-base (closed asphalt):




SYSTEM DESCRIPTION

- total system thickness approx. 13 - 18 mm
- certified in accordance with WORLD ATHLETICS
- certified in accordance with DIN V18035/6, type E
- water-impermeable, pore-filled
- self-levelling, jointless
- hard-wearing, long-lasting
- granulated surface for anti-slip properties
- can handle constant toughest stresses by spikes
- dynamic elasticity
- excellent appearance
- available in many colours

PORPLASTIC *olympic gold*

APPLICATION AND CONSUMPTION

layer	product	consumption (kg/m ²)	thickness (mm)	application
line paint	PORPLASTIC X8090	20 – 30 g/lfm	0.1 – 0.2	spray
UV-sealing (optional)	PORPLASTIC S6020	0.17 – 0.20 per layer	0.1 – 0.2	spray, in 2 layers
wearing layer	PORPLASTIC C570	ca. 2.8	3 – 5	notched squeegee
	PORPLASTIC EPDM (1 – 4 mm)	2.8 net 4.0 total		broadcast, remove excess
2. cast coating	PORPLASTIC C570	ca. 3.0	ca. 5	notched squeegee
	PORPLASTIC EPDM (1 – 4 mm)	3.0 net 3.5 total		broadcast, remove excess
1. cast coating (* depending on substrate)	PORPLASTIC C570	ca. 3.0 – 3.5*	ca. 5	notched squeegee
	PORPLASTIC EPDM (1 – 4 mm)	3.0 net 3.5 total		broadcast, remove excess
primer	PORPLASTIC P270 for asphalt	0.15 – 0.2	ca. 0.1	roll or spray
	VIASOL EP-P210 for concrete, curbs, small areas	ca. 0.5	ca. 0.4	roll



FIELDS OF APPLICATION

- running tracks and run-up tracks for international competitions and tournaments at top-class level
- athletic sport areas type A, B, C
- short distance tracks



TECHNICAL DATA

properties	test norm	result	requirement
tensile strength	WORLD ATHLETICS EN 14877	0.56 N/mm ²	≥ 0.5 N/mm ²
		0.59 N/mm ²	≥ 0.4 N/mm ²
elongation at break	WORLD ATHLETICS EN 14877	63 %	≥ 40 %
		55 %	
shock absorption (23°C)	WORLD ATHLETICS EN 14877	39 %	35-50 % 25-50%
		30 %	
vertical deformation (23°C)	WORLD ATHLETICS EN 14877	2.0 mm	0.6-2.5 mm ≤ 3,0 mm
		1.4 mm	
thickness	WORLD ATHLETICS EN 14877	14.5 mm	≥13 mm (WORLD ATHLETICS) ≥10 mm (EN)
		13 mm	
friction	WORLD ATHLETICS EN 14877	74	>47 80-110 55-110
		wet: 82	
		dry: 85	
resistance to wear	EN 14877	1.62 g	≤ 4.0 g
ageing / color loss	EN 14877	passed / 4	pass / ≥ 3
spike resistance	EN 14877	passed	pass
environmental requirements (DOC, EOX, heavy metals, smell, chloroparaffins, phthalates)	DIN 18035-6 Table A.1	fulfilled	limit values

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore no liability claims can be derived from the system data sheet. As all PORPLASTIC data sheets are updated on a regular basis it is the users responsibility to obtain the most recent issue (see www.porplastic.com or contact us directly). **Date of issue: October 2020** – all technical information is subject to change without prior notice