







VIASOL system data sheet

VIASOL *DECK rapid M (V2) – OS10*

Fast curing car park deck coating system with separate, manually applied waterproofing membrane and wear coat with enhanced crack bridging properties class B 4.2 and IV_{T+V}(-20°C) for multi storey car parks for exposed and intermediate decks and sidewalks on bridges with pedestrian and vehicle traffic.

SYSTEM BUILD-UP

-  Line marking:
e.g. PU or acrylic
-  Sealer:
VIASOL UREA-S6400 P or VIASOL EP-S602
-  Wear coat, fast curing:
VIASOL PU-L315 (L), broadcasted with
QS 0.3 - 0.8 mm or 0.6 - 1.2 mm
-  Highly elastic manually applied
waterproofing membrane:
VIASOL PU-L2000
-  Primer for cementitious substrats:
VIASOL EP-T703 and EP-T703 S
Broadcasted with QS 0.3 - 0.8 mm
-  Substrate: concrete, cementitious screed
and others

SYSTEM THICKNESS

4.5 - 6 mm



SYSTEM HIGHLIGHTS


- High dynamic crack bridging class B4.2 (acc. EN 1062-7) and IV_{T+V} at -20°C (acc. ZTV-BEL-B 3)
- Defined slip resistance and displacement area: R12 V6 or R13 V10

APPLICATION FIELDS

- Exposed car park decks and covered intermediate decks
- Ramps
- Roof decks with car traffic
- Sidewalks on bridges

SYSTEM BENEFITS

- Fast and low temperature curing
- Seamless application with manually applied membrane for reliable waterproofing
- High abrasion resistance
- Good chemical resistance (oil, de-icing salt, petrol, diesel)
- Slip resistant surface for car and pedestrian traffic



Manufacturer:




VIASOL system data sheet

VIASOL *DECK rapid M (V2) – OS10*

APPLICATION AND CONSUMPTION

Layer	Product	Consumption kg/m ²	Broadcasting mm	Thickness mm	Application
Sealer	VIASOL UREA S6400 P	with QS 0.3-0.8 mm: 0.7 – 0.8 kg/m ² with QS 0.6-1.2 mm: 0.8 – 1.0 kg/m ²		0.5	rubber squeegee, roller
alternative	VIASOL EP-S602				
Wear coat, fast curing	VIASOL PU-L315 (L)	1.3 – 1.8	QS 0.3 – 0.8 QS 0.6 – 1.2	1.5 – 2.0	trowel, long-handled squeegee, roller
Highly elastic water proofing manually applied membrane	VIASOL PU-L2000	3.0 – 3.2	none	ca. 2.0	notched trowel
Primer	VIASOL EP-T703	0.3 – 0.5	QS 0.3 – 0.8	ca. 0.3	roller or rubber squeegee
Alternative fast curing	VIASOL EP-T703 S				
Substrate	Cementitious substrates according to the appropriate standards and approvals must be capable of bearing loads and be free of cracks and voids. Pull-off strength ≥ 1.5 N/mm ² , residual moisture content < 4 %-CM, with higher residual moisture and on substrates with moisture from the backside special measures must be taken or a damp proof membrane must be installed. Substrate preparation e.g. grinding or shot blasting, sweeping and vacuum-cleaning is mandatory. Consumptions are calculated with VIASOL quartz sands and fillers. Usage of other quartz sands and fillers can cause changes of consumption and technical data.				
Note	Detailed application instructions are available upon request or refer to the technical product data sheet.				

TECHNICAL DATA

	property	standard	result
	Adhesive strength at T _{NORM}	EN 1542	≥ 2.7 N/mm ²
	Adhesive strength after freeze-thaw with de-icing salt	EN 13687-1 and -2	1.6 N/mm ²
	Dynamic crack bridging (-20°C)	EN 1062-7	B4.2
	Grip and slip resistant	EN 13036-4 DIN 51130	≥ 55 Skt R12 V6 or R13 V10
	Chemical resistance	EN 13529	Test liquids DiBT no. 1, 3, 10
	Abrasion resistance (H22 wheel)	DIN ISO 9352, ASTM D 1044	< 1500 mg /1000 U
	Carbon dioxide permeability	EN 1062-6	class III > 2.500 m
	Water vapour permeability	EN ISO 7783-1 and -2	class III > 200 m
	Water absorption coefficient	EN 1062-3	< 0,01 kg/m ² x h ^{0.5}
	Impact resistance	EN ISO 6772-2	4 Nm – no cracks
	Fire classification	DIN EN 13501-1	B _{fl} -s1

Remark: For further information, please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all VIACOR data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see www.viacor.de or contact us directly) – all technical information is subject to change without prior notice

Manufacturer:

VIACOR Polymer GmbH | Graf-Bentzel-Str.78 | 72108 Rottenburg | Germany | Tel: +49 7472 94999-0 | info@viacor.de | www.viacor.de