

VIASOL system data sheet

VIASOL **UNIFLEX SR**

Slip resistant, tough hard polyurethane resin based coating system, with medium to hard wearing and good mechanical and chemical properties and a wide spectrum of colours and surface structures.

SYSTEM **BUILD-UP**

Optional:
Pigmented matt seal coat on PU-C501:
VIASOL PU-S6005P*



Pigmented top coat
VIASOL EP-S602 or PU-C501*



Wear coat
VIASOL PU-C501 broadcasted with natural quartz sand



Scratch coat, levelling coating
VIASOL PU-C501 (optional)




Primer for cementitious substrates:
VIASOL EP-P260 or other



Substrate: concrete, cementitious screed, asphalt and others

SYSTEM **THICKNESS**

2.5 – 5.0 mm



SYSTEM **HIGHLIGHTS**

- Medium to high wear resistance
- Defined slip resistance
- Hygienic, complies with regulations of food and beverage industry (ISEGA certified)

APPLICATION **FIELDS**

- Production areas in food and beverage industry
- Workshops with liquids
- Catering areas and kitchens
- Hangars and garages and ramps



SYSTEM **BENEFITS**

- Good wear resistant, capable of bearing medium loads
- Low odor, solvent free, does not taint food
- Good abrasion and impact resistance
- Good chemical resistance
- Hygienic, complies with regulations of EU food industry (ISEGA certified)
- Slip resistant surfaces, joint less, seamless
- Impermeable to liquids
- Slightly crack bridging
- Available in many colors
- Good adhesion to concrete and other substrates, with special primers also suitable on substrates with rising water
- Slip resistant surface ca. R10, R11, R12

Manufacturer:

VIACOR Polymer GmbH, Graf-Bentzel-Str.78, D-72108 Rottenburg,
Page 1/2

Tel: +49/7472-94999-0, info@viacor.de, www.viacor.de

version no. 4

issue: 02-2016

VIASOL system data sheet

VIASOL UNIFLEX SR

APPLICATION AND CONSUMPTION

layer	product	consumption (kg/m ²)	sand broadcasting (kg/m ²)	thickness mm	application
optional on PU-C501 pigmented matt seal coat	VIASOL PU-S6005P	0.1 – 0.13	none	0.08 – 0.11	roller
Top coat, pigmented	VIASOL EP-S602	0.5 – 1.0	none	0.3 – 0.8	squeegee and roller
alternative	VIASOL PU-C501	0.5 – 1.0	none	0.3 – 0.8	squeegee and roller
Wear coat broadcasted with natural or coloured quartz sand	VIASOL PU-C501 QS 0.3-0.8 mm or QS 0.6-1.2 mm	1.5 – 3.0	QS 0.3 – 0.8 mm or 0.7 – 1.2 mm in excess	2.5 – 5.5	notched trowel or squeegee
Scratch coat, levelling layer (optional)	VIASOL PU-C501 (fillable 10-20% with VIASOL QNV0)	0.8 – 2.0 + 80 – 400 QNV0	none	0.5 – 2.0	trowel or rubber squeegee / notched trowel or notched squeegee
Primer	VIASOL EP-P260 or VIASOL EP-T703	0.3 – 0.5	QS 0.3 – 0.8 mm 0.5	0.2 – 0.3	roller
Substrate	Cementitious substrates according to the appropriate standards and approvals must be capable of bearing loads and be free of cracks and voids. Pull-off strength ≥ 1.5 N/mm ² , residual moisture content < 4 %-CM, with higher residual moisture and on substrates with moisture from the backside special measures must be taken or a damp proof membrane must be installed. Substrate preparation e.g. grinding or shot blasting, sweeping and vacuum-cleaning is mandatory. Consumptions are calculated with VIASOL quartz sands and fillers. Usage of other quartz sands and fillers can cause changes of consumption and technical data.				
Note	Detailed application instructions are available upon request or refer to the technical product data sheet. (1) for areas with chemical load not suitable				

TECHNICAL DATA



property	standard	result
Compressive strength	EN 196 / ASTM C109	approx. 55 N/mm ²
Flexural strength	EN 196 / ASTM C109	approx. 59 N/mm ²
Shore-Hardness	EN ISO 868	D 65 after 28 d
Adhesive strength	EN ISO 4624	> 2.5 N/mm ² (concrete failure)
Impact strength	EN 13813	≥ 4 Nm (IR4)
Wear resistance (Taber)	EN ISO 5470-1	≤ 80 mg
Solvent free / Total solid	Test method "Deutsche Bauchemie"	≤ 1 % (not valid for water based seal coat)
Chemical Resistance	EN ISO 2812-1	Test liquids 3, 10, 11 (more see chemical resistance list)
Fire Resistance	EN 13501-1	B _{fl} -S1 (System VIASOL UNIFLEX)

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore no liability claims can be derived from the system data sheet. As all VIACOR data sheets are updated on a regular basis it is the users responsibility to obtain the most recent issue (see www.viacor.de or contact us directly)– all technical information is subject to change without prior notice

Manufacturer:

VIACOR Polymer GmbH, Graf-Bentzel-Str.78, D-72108 Rottenburg,
Page 2/2

Tel: +49/7472-94999-0, info@viacor.de, www.viacor.de

version no. 4

issue: 02-2016