

Product 01020310 2-C-EP primer, fast curing, prefilled, solvent free, whitish

1 General Data

Fields of application

VIASOL EP-P203 S can be used as a fast curing moisture barrier for industrial floors with increased residual subsoil humidity in cement-based systems of up to 6 % and as a priming coat for VIASOL epoxy and polyurethane products.

Product description

VIASOL EP-P203 S is a prefilled, ready-to-use, whitish, two-component priming coat having a solvent free resin base. VIASOL EP-P203 S is fast and low temperature curing.

Technical support

For system build up possibilities and detailed information relating to the laying of VIASOL products, please refer to the VIASOL System Planner or contact VIACOR Polymer GmbH directly.

Phone: +49 (0)7472-949990

E-Mail: info@viacor.de

(A) Technical data	
Liquid mixture (A+B)	
1. Solids content	99.5%
2. Density (20°C)	1.5 g/cm ³
3. Viscosity (20°C)	1200–2000 mPas
4. Packaging size (2-component container)	30 kg (24 kg A + 6 kg B)
5. Shelf life	24 months in closed original container
6. storage	Dry at 10–25°C, avoid direct sunlight

(B) Technical data	
Cured material	
1. Adhesive strength (DIN EN ISO 4624)	> 2.5 N/mm ² (concrete failure)

Product 01020310 2-C-EP primer, fast curing, prefilled, solvent free, whitish

2 Application method

Substrate preparation

The substrate must be prepared by vacuum shot blasting. Rough contaminations can be removed by grinding. VIASOL EP-P203 S can be applied directly to the surface if the substrate moisture content does not exceed max. 6 % and the surface is absorbent and free from puddles. There should be no water in the pores. The surface must have an adhesive strength of minimum 1.5 N/mm². All traces of contaminants such as oils, fats, greases, paint residues, chemicals, algae and laitance should be removed. Cracks and hollow spots must be properly remedied. Before retopping old coatings, please contact our technical support.

Application

The product is delivered in 2 component containers in the exact mixing ratio. Before starting the application, the material has to be warmed to ambient temperature (air and floor temperature). For 2 component containers, the entire contents of the B-component container is emptied into the A-component container. After mixing with a suitable electrical stirrer for approx. 3–4 minutes the mixture is poured into another container and stirred again briefly. The inclusion of air in the stirring process is to be avoided. Shall vertical surfaces are coated, 0.5-2% thixotropic agent, e.g. VIASOL X955 must be added.

For substrates with residual moisture contents of less than 4 CM% the product is applied in one layer with a squeegee or a trowel and rerolled. For substrates with residual moisture 4-6% CM it must be paid particular attention to a film-forming, closed surface. If pores are still in the first layer, VIASOL EP-P203 S must be applied about 4 hours after the first application again. Here it can be rolled using a short pile roller. To improve the adhesion to the next layer the second VIASOL EP-P203 S layer can easily be sprinkled with quartz sand (about 800 g/m² VIASOL QS 0.3-0.8 mm)

For cleaning of tools and other contaminations VIASOL SO-X10 tool cleaner is used.

Overcoating

Overcoating has to take place within 24 hours after application of the layer. Grinding would destroy the closed film of the priming layer.

(C) Technical data

Liquid mixture (A+B)

1.	Mixing ratio A : B	100 : 25 by weight (kg)
2.	Working time (20°C) Pot life (20°C)	approx. 12 minutes approx. 7 minutes
3.	Application temperature:	5 – 25°C (min. 3°C above dew point)
4.	Material consumption	300–700 g/m ² per layer
5.	Foot traffic (20 °C)	after 3 – 5 hours
6.	Following coating (20°C)	within 3 – 18 hours
7.	fully capable of withstanding stress: mechanical (20°C) chemical (20°C)	after 2 days after 5 days

Manufacturer:

VIACOR Polymer GmbH, Graf-Bentzel-Str.78, D-72108 Rottenburg, Tel: +49 7472 94999-0, info@viacor.de, www.viacor.de

Product 01020310 2-C-EP primer, fast curing, prefilled, solvent free, whitish

3 Further information

CE-Mark



CE-Mark according to EN 13813

EN 13813: 2003-01, Screed material and floor screeds - Screed materials - Properties and requirements is the basis for requirements for floor screeds used in indoor flooring constructions. Resin coatings and sealer are also subject to this norm.

Details see CE-conformity mark and conformity declaration.

Decopaint-Guidelines (EU 2004/42/EG)

The maximum allowable VOC content for Product category IIA j Type Lb in the ready-to-use state is stage II (from 2010) < 500 g/l VOC.

In the ready-to-use state this product contains less than 500 g/l VOC.

Warnings and precautions

Information relating to the safe handling of this product can be found in the Material Safety Data Sheet. Local regulations concerning the safe handling of epoxy resin based coating materials must be observed.

Suitable protective clothing including suitable eye protection must be worn.

Disclaimer

All information in this technical data sheet is based on our current knowledge and experience. This does not release the applicator from performing their own tests as many application factors, beyond our control, affect the application of our product. No guarantee of characteristics or suitability for a special purpose can be derived from this information. All present data, descriptions, drawings, photos, ratios, weights etc. are subject to change without prior notice and do not represent contracted characteristics of the product.

Due to different materials, sub-bases and working conditions, no guarantee of an application result or any liability claims can be derived from these details or from an unwritten technical advice except for liability claims based on:

-damage to life, body or health resulting from a negligent violation of obligations or a deliberate or negligent violation of obligation of a legal representative or assistant and

-if we are charged with intention or gross negligence.

The user has to test the products for their intended use. The user is responsible for following existing laws and orders and for observing third party trade mark rights.

As all VIACOR data sheets are updated on a regular basis it is the users responsibility to obtain the most recent issue (see www.viacor.de).